

Board

TEMPTATION HEAVEN

Substance	ISO 536	g/m2	115	135	150	170
Caliper	ISO 534	µm	105	125	140	160
Bulk	ISO 534	cm3/g	0,91	0,93	0,93	0,94
Smoothness Bekk	ISO 5627	s	120	120	120	120
Gloss Gardner	ISO 8254-1	%	7	7	7	7
Whiteness CIE	ISO 11475	%	155	155	155	155
Brightness ISO	ISO 2470 (D65)	%	107	107	107	107
Opacity ISO	ISO 2471	%	95	97	97	98
Relative moisture	ISO 287	%	50	50	50	50



Finishing	Matt
Printing method	Sheet-fed offset
Applications	

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

SBS cardboard

Board

TEMPTATION HEAVEN

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m2	200	250		
Caliper	ISO 534	µm	188	250		
Bulk	ISO 534	cm3/g	0,94	1,00		
Smoothness Bekk	ISO 5627	s	120	120		
Gloss Gardner	ISO 8254-1	%	7	7		
Whiteness CIE	ISO 11475	%	155	155		
Brightness ISO	ISO 2470 (D65)	%	107	107		
Opacity ISO	ISO 2471	%	98	99		
Relative moisture	ISO 287	%	50	50		



Notes:

FinishingMatt

Printing methodSheet-fed offset

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

SBS cardboard

Board

TEMPTATION HEAVEN HS

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m2	300	400		
Caliper	ISO 534	µm	310	440		
Bulk	ISO 534	cm3/g	1,03	1,10		
Smoothness Bekk	ISO 5627	s	120	120		
Gloss Gardner	ISO 8254-1	%	7	7		
Whiteness CIE	ISO 11475	%	155	155		
Brightness ISO	ISO 2470 (D65)	%	107	107		
Opacity ISO	ISO 2471	%	99	99		
Relative moisture	ISO 287	%	50	50		



Notes:

Finishing **Matt**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.